

AFS		THREADS	ØΑ	ØВ	С	Н	S	(V)	W	AXIAL TENSILE		
PRODUCTS PART NO.		PER AS8879	MAX	MIN	MIN	MAX	MIN			STRENGTH Ibf MIN	TORQUE lbf-IN	WEIGHT lbs/100
H38-	08	.1640-32UNJC-3B	.284	.264	.243	.250	.070	.025	.221 .212	2,153	1.5-11	.16
	3	.1900-32UNJF-3B	.350	.325	.279		.080	.040	.251 .243	3,150	2.0-15	.23
	4	.2500-28UNJF-3B	.440	.410	.351	.328	.095	.050	.313 .305	5,868	3.5-30	.41
	5	.3125-24UNJF-3B	.525	.495	.421	.360	.110	.060	.376 .367	9,432	6.5-60	.69
	6	.3750-24UNJF-3B	.598	.559	.496	.458	.155	.070	.439 .430	14,562	9.5-80	1.00
	7	.4375-20UNJF-3B	.692	.652	.638	.531	.170	.090	.564 .553	19,620	14-100	1.94
	8	.5000-20UNJF-3B	.786	.746	.707	.578	.185	.110	.627 .616	26,748	30-150	2.60
	9	.5625-18UNJF-3B	.880	.840	.775	.633	.205	.115	.690 .679	33,984	50-200	3.28
	10	.6250-18UNJF-3B	.970	.930	.881	.687	.235	.120	.783 .772	43,200	50-300	4.13
	12	.7500-16UNJF-3B	1.250	1.200	1.059	.796	.310	.140	.940 .928	63,236	50-400	8.60

MATERIAL:

WASPALOY PER AMS5709 (UNS N07001).

FINISH:

SILVER PLATE PER AMS2411.

PERFORMANCE:

AS7253, EXCEPT AS FOLLOWS:

A) ALL TESTING TO BE PERFORMED ON .003 REDUCED P.D. BOLTS.

B) AXIAL TENSILE STRENGTH AS TABULUATED.

TEMPERATURE:

1400 °F.

NOTES:

1. C AND W DIMENSIONS APPLY BEFORE FORMING SELF LOCKING FEATURE.

